

address STAEDTLER Mars GmbH & Co. KG
 Moosackerstr. 3
 90427 Nürnberg
 phone +49 911 93 65 - 888
 fax +49 911 93 65 - 769
 internet www.staedtler.de
 e-mail service@staedtler.com



Article description	
FIMO KIDS 8030	Made in Germany

Constituents	
Binding agent:	Polyvinyl chloride
Special softening agent:	Not classified as hazardous in accordance with the European legislation. Recommended by the CSTEE (Comité Scientifique de Toxicologie, Ecotoxicologie et l'Environnement) European Scientific Committee on Toxicity, Ecotoxicity and Environment
Filler:	Inorganic fillers, e.g. chalk
Colouring agent:	Colour pigments
Packaging:	Standard block,: PE-film, Blister card: PET with paper sheet
Accessories	Modelling stick: PP, modelling pad: PE

PP = polypropylene, PE = polyethylene, PET = polyester

Conformity	
CE	The products conform to the European Standard 2009/48/EG 'safety of toys' and therefore bear the CE symbol.
EN71	Tests are in accordance with testing rules contained in European Standard EN 71:
EN71/1	EN71/1 Mechanical and physical properties
EN71/3	EN71/3 Specification for migration of certain elements and
EN71/5	EN71/5 Chemical toys (sets) other than experimental sets.
	To be tested: Oven-hardening modeling clay and packaging. Safety instructions are defined by the standard.
The modelling clays meet the Regulations (EG) No. 1907/2006 (REACH) and No. 1272/2008 (CLP) concerning the Registration, Evaluation, Authorization and Restriction of Chemicals. In accordance with REACH Regulation 1907/2006/EC, Article 33, you will find our current articles subject to mandatory reporting under the following link https://www.staedtler.com/REACH	
ASTM D-4236 FIMO KIDS is tested by ACMI (Art & Creative Material Institute) and conforms to the US-Standard ASTM D-4236. According to the standard, a qualified external toxicologist tests the products.	
Additional product inspections: No emissions during a curing temperature of max. 130°C/266°F and a curing time of 30 min (Tested by an accredited laboratory).	

Usage notes
As an optimal curing temperature / curing time is recommended: 110°C (230°F) / 30 min. Please observe the instructions for use. The hardening of the modelling clay is based on a gelling process in which the plastic powder is dissolved in the plasticizer by heat. FIMO KIDS is ideal for educational purposes in schools as well as for hobby applications.

Staedtler has been certified to ISO 9001 and ISO 14001 and considered in the selection of raw materials and their processing in the relevant national and international laws to protect the users.