

address STAEDTLER Mars GmbH & Co. KG
 Moosackerstr. 3
 90427 Nürnberg
 phone +49 911 93 65 - 888
 fax +49 911 93 65 - 769
 internet www.staedtler.de
 e-mail service@staedtler.com



Article description	
FIMO leather-effect 8010, 8019	Made in Germany

Constituents	
Binding agent:	Polyvinyl chloride
Special softening agent:	Not classified as hazardous in accordance with the European legislation. Recommended by the CSTE (Comité Scientifique de Toxicologie, Ecotoxicologie et l'Environnement) European Scientific Committee on Toxicity, Ecotoxicity and Environment.
Filler:	Inorganic fillers, e.g. chalk
Colouring agent:	Colour pigments
Packaging :	Standard block: PE-film

PE= polyethylene

Conformity	
The modelling clays meet the Regulations (EG) No. 1907/2006 (REACH) and No. 1272/2008 (CLP) concerning the Registration, Evaluation, Authorization and Restriction of Chemicals. In accordance with REACH Regulation 1907/2006/EC, Article 33, you will find our current articles subject to mandatory reporting under the following link https://www.staedtler.com/REACH	
Additional product inspections: No emissions during a curing temperature of max. 130°C/266°F and a curing time of 30 min (Tested by an accredited laboratory).	
ASTM D-4236 FIMO leather effect are tested by ACMI (Art & Creative Material Institute) and conform to the US-Standard ASTM D-4236. According to the standard, a qualified external toxicologist tests the products.	

Usage notes	
As an optimal curing temperature / curing time is recommended: 130°C (266°F) / 30 min. Please observe the instructions for use. The hardening of the modelling clay is based on a gelling process in which the plastic powder is dissolved in the plasticizer by heat. FIMO leather-effect is ideal for art, recreation and hobby. FIMO is a craft product, NOT a toy.	

Staedtler has been certified to ISO 9001 and ISO 14001 and considered in the selection of raw materials and their processing in the relevant national and international laws to protect the users.